

Geprüfte  
Baustoffe aus  
natürlichen und  
nachwachsenden  
Rohstoffen...

**Hessler**

KALK & PUTZ

# Das Hessler Kalksystem.

Qualität seit 1881

Hessler Kalkwerke GmbH · 69154 Wiesloch · Postfach 1345 · Tel. 062 22/92 75-0

## HP 9600 Biogrund fein

### Composition:

(full material declaration)

**HP 9600 Bio Primer, fine consists of** white hydrated lime, china clay, casein, marble powder, cellulose fibres and methyl cellulose. Contains no titanium oxide.

HP 9600 contains no preservatives and is highly water vapour resistant.

### Application range:

HP 9600 is used as **primer** for indoors. It is especially suited for preparing different substrates for **paint coatings** as it regulates the absorbency of the substrate and has no granulation. Can be used on drywall boards and existing absorbent substrates (lime, lime cement, gypsum, clay, etc.).

### Application:

Mix the contents of the bucket with **approx. 7 litres of water** and stir without lumps until the desired consistency is obtained. Use a suitable stirrer for this purpose. Allow to stand for approx. 30 minutes and stir again. Apply by roller or ceiling brush. The **drying time** amounts to approx. 24 hours (depending on e.g. temperature and air humidity). Immediately dissolve and remove paint splashes on surrounding surfaces with water.

### Consumption rate:

A 5.0 kg bucket makes approx. 10 litres of liquid primer.

**Spreading rate:** approx. 35 m<sup>2</sup> / bucket (approx. 200 - 350 g / m<sup>2</sup>) (depending on nature of substrate)

### Please note:

DIN 18550 and DIN 18350 must be observed for assessing and preparing the plaster base. The plaster base must be absorbent, dry and free of dust and loose residues. Remove wallpaper, plaster fleece and old wallpaper paste or formwork oil residues entirely. Not suitable for outdoors. The air and/or object temperature must be **above 5 °C**. Adequate **ventilation** must be ensured.

HP 9600 may only be used in its original state without any admixture.

<b>Packaging unit:</b>	5.0 kg buckets, 24 buckets / pallet Weight: approx. 120 kg / pallet
<b>Storage:</b>	Dry, shelf life at least 12 months in closed packaging
<b>Quality monitoring:</b>	HP 9600 is continuously monitored in the in-house laboratory for compliance with its composition and properties.
<b>Safety advice:</b>	Protect skin and eyes due to strong alkalinity. In case of contact, rinse thoroughly with water. In case of eye contact, consult a doctor immediately.

For more information, please contact us by phone or in writing at:  
[info@hessler-kalkwerk.de](mailto:info@hessler-kalkwerk.de), or at: +49 6222/9275-0. We will be glad to assist you!

This information is based on our experience and does not take into account any specific case. No claims for damages can therefore be derived from it. All information without guarantee. Errors, typing errors and changes reserved.